

中国认可 国际互 认 检测 TESTING CNAS L0472

TEST REPORT

No. Zb2018Z0113

Standard code : GA44-2015

Product name


FTK-Q/F Fire Fighting Helmet

Authentication

Guangdong Youright Trade Co., Ltd.



Name: China National Fire Equipment Quality Supervision Centre Address: 391 Xi Huan Road, Xinzhuang Shanghai, P.R.China Telephone: 86-21-54959866-6102 Fax: 86-21-54959907 Post Code: 201199 Website: http://www.xfjyzx.com E-mail: <u>fireshnc@sh163.net</u>



No:Zb2018Z0113 Standard code : GA44-2015

Model.: FTK-Q/F

| Product nameplate content | |
|--|---|
| product name | Fire helmet |
| Model specification | FTK-Q/F |
| Producer and/or production company | Guangdong Youright Trade Co., Ltd. |
| Identification number or manufacturing date | Yes |
| Inspection mark | Yes |
| Executive standard | GA44-2015 |
| Warning words | / |
| \Box . Product feature description | |
| Cap shell molding process | Injection molding |
| Ξ . Description of key product parts | |
| 1. Cap shell material name, model specification, | Flame-retardant reinforced nylon (Z-SFRPA6), B909-H |
| material supplier | Suzhou Ebon Engineering Plastic Co., Ltd. |
| 2. Cap shell model specification, manufacturer | MK-03 |
| | Changzhou Aoxin Plastic Co., Ltd |
| 3. Buffer layer material name, model specification, | (AX) Juxing, YD-330N |
| material supplier | Wuxi Huihuang Furniture Fittings Factory |
| 4. Buffer layer model specification, manufacturer | HC-03 |
| | Changzhou Aoxin Plastic Co., Ltd. (AX) |
| 5. The name of the cap support material, model | Polyester webbing, (50 soil 2.5) mm |
| specification, material supplier | Jiangshan Xiang'an Rope Processing Factory |
| 6. Cap holder model specification, manufacturer | MT-03 |
| | Zhejiang Dongan Fire Equipment Technology Co., Ltd. |
| | (DA) |
| 7. The name of the material, model specification, and | Flame-retardant webbing, XFZD Shanghai Mingqian |
| material supplier are issued under the | Industrial Co., Ltd. |
| 8. Mask material name, model specification, material | Polyphenylene PPSU, 3010 Shanghai Speed Rubber & |
| supplier | Plastic Co., Ltd. |
| 9. Mask model specifications, manufacturer | MZ-03 |
| | Changzhou Aoxin Plastic Co., Ltd. (AX) |
| 10. Shawl material name, model specification, material | Aramid aluminum foil cloth, aramid multi-component |
| supplier | flame-retardant fabric, GB200, XF360 Shanghai |
| | Mingqian Industrial Co., Ltd. |
| Consistency check conclusion: compliant | |

No:Zb2018Z0113 Standard code : GA44-2015

Model.: FTK-Q/F

| NO | Inspection item | | Standard request | Inpection | | |
|----|------------------------|------------------------------------|---|-----------|--|--|
| | | ···· | | results | | |
| 1 | Material and structure | | It shall meet the requirements of 5.1 | | | |
| 2 | appearance re | equirement | It shall meet the requirements of 5.2 | | | |
| | | TT: -1- | Maximum impact force≤3780N | | | |
| | | temperature pretreatment | No debris shall fall off the cap shell, no damage or fracture shall be caused to the cap bracket, and no damage or fracture shall be caused to the connecting mechanism between the cap cap and the cap shell | qualified | | |
| | | | Maximum impact force≤3780N | | | |
| | Impact | pretreatment | No debris shall fall off the cap shell, no damage or fracture shall be caused to the cap bracket, and no damage or fracture shall be caused to the connecting mechanism between the cap cap and the cap shell | qualified | | |
| 3 | absorption | | Maximum impact force≤3780N | 3515.6 | | |
| | property | Low temperature pretreatment | No debris shall fall off the cap shell, no damage or fracture shall be caused to the cap bracket, and no damage or fracture shall be caused to the connecting mechanism between the cap cap and the cap shell | qualified | | |
| | | | Maximum impact force≤3780N | 2790.5 | | |
| | | pretreatment | No debris shall fall off the cap shell, no damage or fracture shall be caused to the cap bracket, and no damage or fracture shall be caused to the connecting mechanism between the cap cap and the cap shell | qualified | | |
| | | The top of hat | Maximum impact acceleration≤150gn | 130.1 | | |
| | | The front of the hat | Maximum impact acceleration≤400gn | 278.9 | | |
| | | | accelerated speed >150gn, duration<6ms | 5 | | |
| | | | accelerated speed >200gn, duration<3ms | 2.2 | | |
| 4 | | the hat | Maximum impact acceleration≤400gn | 309.4 | | |
| | | | accelerated speed >150gn, duration<6ms | 4.9 | | |
| | | | accelerated speed >200gn, duration<3ms | 2.3 | | |
| | | The back of the hat | Maximum impact acceleration≤400gn | 275.7 | | |
| | | | accelerated speed >150gn, duration<6ms | 4.8 | | |
| | | | accelerated speed >200gn, duration<3ms | 2.1 | | |
| 5 | Penetration resistance | | The steel cone shall not penetrate the helmet and make contact with the head die | qualified | | |
| 6 | Fire resistance | | After the fire source leaves the cap, the cap flame should be extinguished within 5 seconds | qualified | | |

| No. | Inspection item | | | Standard request | Inspection result | |
|-----|-------------------------------------|---------------|--|---|----------------------|-----------|
| | | chin strap | The length of the damaged (mm) | ≤100 | 9 | |
| | | | after flame time (s) | ≤2 | 0 | |
| | | | The test phenomenon | There should be no melting, dripping phenomenon | qualified | |
| | | wraps | The length of the damaged (mm) ≤ 100 | | 26 | |
| 7 | flame retardation | | wraps after flame time $(s) \leq 2$ | | 0 | |
| | veil | | The test phenomenon There should be no melting, dripping phenomenon | | qualified | |
| | | | after flame time (s) | ≤5 | 0 | |
| | | veil | The test phenomenon | There should be no melting, dripping phenomenon | qualified | |
| | resistance to effect of heat | | | The cap shall not touch the headform and shall not be significantly deformed | | |
| | | | | There shall be no visible deformation or damage to the cap, cap rest, buffer layer and chin band | | qualified |
| 8 | | | | resistance to effect of heat Cap adjusting devices, chin strap locking devices, accessories and hardware shall maintain their original functions | | |
| | | | | No part shall be ignited or melted | qualified | |
| | | | | The mask should be free from obvious deformation and damage | | |
| 9 | dielectric protecties | | | Cap leakage current ≤3.0mA | 0.9 | |
| | | | | Extension length≤20mm | 18.1 | |
| 10 | Tensile strength of chin band | | | There should be no fracture of the chin band, loose connectors and loose buckles | qualified | |
| | | | | Maximum deformation of cap case≤40mm | 33.5 | |
| 11 | | Lateral | rigidity | Deformation after unloading≤15mm | 3.1 | |
| | | | | The cap should not be broken off | qualified | |
| 12 | | | Stability of helmet wearing device The requirements of 5.3.10 shall be met | | qualified | |
| 13 | Corrosion resistance of metal parts | | | The requirements of 5.3.11 shall be met | qualified | |
| 14 | | | | There should be no breakage | qualified | |
| 15 | - | | | There should be no breakage | qualified | |

No:Zb2018Z0113 Standard code : GA44-2015

Model.: FTK-Q/F

| NO. | Test items | | | Standard request | Inspection result | |
|-----|-----------------------------------|--|-------------------------|--------------------------------------|-------------------|------|
| | Optical performance of mask | spherical equivalent | | -0.12~0.12 | -0.07 | |
| | | astigmatic power | | ≤0.12 | 0.08 | |
| | | Spherical degree local variation | | | ≤0.09 | 0.03 |
| 16 | | Difference of prism | horizontal direction | Basal outward | ≤1 | 0.65 |
| 10 | | | | Basal inward | ≤0.25 | / |
| | | | vertica | al direction | ≤0.25 | 0.14 |
| | | Mask transmittance | | without color | ≥85 | / |
| | | | | light color | ≥43 | 60.1 |
| 17 | The shawl is | waterproof and resistant to hydrostatic pressure | | | ≥17 | >17 |
| | view | Left level | | ≥105 | >105 | |
| 18 | | The right level | | | >105 | |
| 10 | | up | | ≥7 | >7 | |
| | | down | | | ≥45 | >45 |
| 19 | quality | | | ≤1800 | 1517 | |
| 20 | mark | | | The requirements of 8.1 shall be met | qualified | |









SPECIFICATION

| Products Name | Fire Fighting Helmet (Model : FTK-Q/F) |
|---------------|---|
| Color | RED |
| Material | Flame-retardant reinforced nylon(Z- SFRPA6),B909-H |
| Application | Petroleum/power plant/construction/mine/port |
| Feature | Impact resistance/high strength/strong toughness/electrical insulation |